

Oil-Well Packer

RAW MATERIAL	FUNCTION	PARTS
Nitrile 1051	Base Polymer	100
Birla N-550	Reinforcement	70
Acme-Hardesty Triple Pressed Stearic Acid	Accelerator	1
Zochem Zoco 102	Accelerator	5
H.M. Royal RM 98	Curing Agent	0.4
SI Group Ethanox 310	Antioxidant	2
ESO	Plasticizer	5
ZDMC	Accelerator	1.5
MBTS	Accelerator	0.6



Interested in learning more?

At H.M. Royal, we have been working on formulas for over 90 years. Let one of our technical specialists select the right product for your formulation.